


AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:


LISTING OF CLAIMS:

1 - 7. (canceled).

8. (currently amended): A method of producing a vinyl ether group-containing (meth) acrylic ester represented by the following formula (1):



in the formula, R^1 represents a hydrogen atom or a methyl group, R^2 represents a straight, branched or cyclic alkylene group containing 2 to 20 carbon atoms, an alkylene group containing 2 to 20 carbon atoms and having at least one oxygen atom in the form of an ether linkage and/or an ester linkage within the structure thereof, or an aromatic group which contains 6 to 11 carbon atoms and may optionally be substituted, R^3 represents a hydrogen atom, a straight, branched or cyclic alkyl group containing 1 to 10 carbon atoms, or an aromatic group which contains 6 to 11 carbon atoms and may optionally be substituted, and which comprises reacting a hydroxyl group-containing vinyl ether represented by the following formula (2):




in the formula, R^2 represents a straight, branched or cyclic alkylene group containing 2 to 20 carbon atoms, an alkylene group containing 2 to 20 carbon atoms and having at least one oxygen atom in the form of an ether linkage and/or an ester linkage within the structure thereof,

or an aromatic group which contains 6 to 11 carbon atoms and may optionally be substituted, and R³ represents a hydrogen atom, a straight, branched or cyclic alkyl group containing 1 to 10 carbon atoms, or an aromatic group which contains 6 to 11 carbon atoms and may optionally be substituted,

with a (meth) acrylic ester represented by the following formula (3):




in the formula, R¹ represents a hydrogen atom or a methyl group and R⁴ represents a straight, branched or cyclic alkyl group containing 1 to 8 carbon atoms and ~~said hydroxyl group-containing vinyl ether containing~~ wherein said hydroxyl group-containing vinyl ether contains, as an impurity, at least one compound selected from the group consisting of a divinyl ether represented by the following formula (4):




in the formula, R² represents a straight, branched or cyclic alkylene group containing 2 to 20 carbon atoms, an alkylene group containing 2 to 20 carbon atoms and having at least one oxygen atom in the form of an ether linkage and/or an ester linkage within the structure thereof, or an aromatic group which contains 6 to 11 carbon atoms and may optionally be substituted, and the two R³ groups are the same or different and each represents a hydrogen atom, a straight, branched or cyclic alkyl group containing 1 to 10 carbon atoms, or an aromatic group which contains 6 to 11 carbon atoms and may optionally be substituted,

a 2-substituted-1, 3-dioxo compound represented by the following formula (5):



in the formula, R^2 represents a straight, branched or cyclic alkylene group containing 2 to 20 carbon atoms, an alkylene group containing 2 to 20 carbon atoms and having at least one oxygen atom in the form of an ether linkage and/or an ester linkage within the structure thereof, or an aromatic group which contains 6 to 11 carbon atoms and may optionally be substituted, and R^3 represents a hydrogen atom, a straight, branched or cyclic alkyl group containing 1 to 10 carbon atoms, or an aromatic group which contains 6 to 11 carbon atoms, and may optionally be substituted, and

an unsaturated bond-containing vinyl ether represented by the following formula (6):



in the formula, R^3 represents a hydrogen atom, a straight, branched or cyclic alkyl group containing 1 to 10 carbon atoms, or an aromatic group which contains 6 to 11 carbon atoms and may optionally be substituted; R^5 represents an organic residue containing an unsaturated bond represented by $-CR^6=CR^7$; and R^6 and R^7 are the same or different and each represents a hydrogen atom or an organic residue.

9. (canceled).

10. (previously presented): The method of producing a vinyl ether group-containing (meth) acrylic ester according to claim 8,

wherein the vinyl ether group-containing (meth) acrylic ester is produced in an atmosphere such that a molecular oxygen concentration is 0.01 to 10% by volume.

11 - 12. (canceled).

13. (currently amended): A method of purifying a vinyl ether group-containing (meth) acrylic ester prepared by the method of producing a vinyl ether group-containing (meth) acrylic ester according to claim 8,

which comprises carrying out said method of purifying a vinyl ether group-containing (meth) acrylic ester in an atmosphere such that a molecular oxygen concentration in the gaseous phase in the purification system is 0.01 to 10% by volume, wherein said purification of a vinyl ether group-containing (meth) acrylic esters is carried out in the manner of distillation purification.

14 - 21. (canceled).